



DiamondCoat[®]

Sealer Tint Base

Full colour coating system to rejuvenate concrete, paving and masonry.

DESCRIPTION

Crommelin[®] DiamondCoat[®] Sealer Tint Base is designed to recolour, rejuvenate, seal and protect new and old concrete and paving. Crommelin[®] DiamondCoat[®] Sealer Tint Base may be tinted to a range of colours to suit any application.

Crommelin[®] DiamondCoat[®] Sealer Tint Base, when mixed with your chosen tint colour, will provide a solid colour that out performs traditional paving paint alternatives and is available in satin and gloss finishes.

FEATURES AND BENEFITS

- Colour, seal, protect and rejuvenate concrete surfaces.
- Penetrates up to 3mm into substrate.
- Simple surface preparation and application.
- Will not flake or peel, like traditional paving paint.
- Long term UV stability, non yellowing.
- Maximum stain resistance.
- Resists oil, grease and general dirt pick up.

AREAS OF USE

DiamondCoat[®] Sealer Tint Base is suitable for use on most paving and concrete surfaces, and is ideally suited to:

- All previously uncoated areas of concrete requiring a stain-resistant durable coloured finish.
- Driveways.
- Paths & Walkways.
- Internal Floors.
- Garage Floors.
- Alfresco Areas.



SUITABLE SUBSTRATES

DiamondCoat® Sealer Tint Base is suitable for use on the following surfaces:

- Concrete – including stamped, coloured and stencilled.
- Stone – most medium to high porosity stone.
- Paving – most natural and reconstituted paving, excluding clay/brick paving.

Note: not suitable on some terracotta and low porosity natural stone surfaces. In some instances the sealer may not penetrate effectively. Test area is recommended before final application.

APPLICATION TOOLS

- Crommelin® Contractor Membrane Applicator Brush – 100mm, 75mm.
- Crommelin® Contractor Membrane Roller Cover – 230mm.
- Lambswool applicator.

SURFACE PREPARATION

Full surface preparation instructions can be found at www.crommelin.com.au/full-instructions/

Surfaces must be clean, sound and free from dust, grease, curing compounds, release agents, loose particles, efflorescence, concrete laitance or any other contaminants. Use Crommelin® DiamondCoat® Clean N Prep to remove grease, oils etc

- **All surfaces to be coated must be sound.** Any areas of loose or friable substrate must be removed and repaired by a suitable repair mortar.
- If acid etching has taken place, ensure neutralisation of the area and thorough rinsing has been conducted.
- **All surfaces to be coated must be dry.** A moisture test is required 100% of the time to ascertain if the substrate is dry enough to coat. Electronic moisture meters are recommended, however a simple test may be performed as per below.

Simple Moisture Test: Place a 300mm x 300mm piece of black plastic or rubber mat on the area to be coated at the hottest part of the day. After 2 hours, remove and inspect. If any condensation is present on the underside of the plastic, or the substrate has darkened, then it is too wet to coat. Be patient, allow to dry further and repeat test until no moisture is detected.

- If area has been previously sealed, ensure coating compatibility. If in doubt, remove existing coating.
- Ensure any areas where coating is not required are suitably protected with plastic drop sheets or similar.

PRODUCT PREPARATION

- **8L DiamondCoat® Tint Base** is designed to be mixed with **1L DiamondCoat Tint**, producing 9L of tinted sealer.
- Separately stir both the tins before combining and continuing to stir mechanically for 3 minutes, ensuring no air is trapped.
- Ensure that a homogenous colour is achieved, without any colour streaking.



APPLICATION CONDITIONS

- Do not apply if surface/ambient temperatures are too high or too low. Recommended application temperature range 5⁰c - 35⁰c.
- Do not apply if humidity is too high, or likely to be during the initial cure phase. Maximum recommended humidity during application and cure is 85%.
- Do not apply if rain is expected within 48 hours, weather details may be checked at <http://www.bom.gov.au>.

APPLICATION PROCESS

Full application instructions can be found at www.crommelin.com.au/full-instructions/

- Apply a trial patch before full application, to assess sealer adhesion, substrate colour enhancement, gloss level and slip resistance.
- Ensure that all application tools are clean and lint free.
- Apply the first coat of **DiamondCoat® Sealer Tint Base** with sufficient product to thoroughly coat the surface leaving a fine and consistent film.
- When the first coat is sufficiently dry (to touch), apply a second coat ensuring all product applied consistently covers the first coat.
- Where applying to sloping or grip-critical surfaces, **Crommelin® DiamondCoat® Anti Slip** can be used to improve traction in dry or wet conditions.
- Paving sealers may become cloudy in areas affected by rising damp or where too much sealer has been applied. In this situation liberally apply **Crommelin® DiamondCoat® Solvent** to the affected area and work in with a brush for several minutes until the surface exhibits a dark wet look. Allow to dry, repeat as necessary.

RE-COAT/CURE TIME

- Recoat time: 2-4 hours.
- Light foot traffic: 10-12 hours.
- Full cure: 7 days.

COVERAGE

- High Porosity Substrate: 4m²-8m² per litre.
- Medium Porosity Substrate: 8m²-12m² per litre.

Note: Coverage rates are dependent upon the porosity of the surface to be treated and are offered as a guide only. A sample test area is recommended to determine specific coverage rates.

Porosity Testing: Place a few drops of water on the surface you wish to test. Leave for 2 minutes and dab dry with paper towel. If darker, wet spots remain the surface is porous and can be sealed. If the surface does not darken or show signs of penetrations, it is too dense and should not be sealed with DiamondCoat® Sealer.

CLEAN UP

- Clean all equipment with **Crommelin® DiamondCoat® Solvent** before product dries.



SIZES

DiamondCoat® Sealer Tint Base is available in 3.5L and 8L pails in Satin or Gloss finish.

RELATED PRODUCTS

- Crommelin® Moisture Meter.
- Crommelin® Contractor Membrane Applicator Brush – 100mm, 75mm.
- Crommelin® Contractor Membrane Roller Cover – 230mm.
- Crommelin® Diamondcoat® Solvent.
- Crommelin® Diamondcoat® Clean N Prep.
- Crommelin® Diamondcoat® Tint.

MAINTENANCE AND REPAIR

- Protect **DiamondCoat® Sealer Tint Base** from harsh chemicals, abrasion and other potentially damaging conditions.
- The use of door mats is recommended at all entry points.
- Regular cleaning of the coated surface to remove abrasive contaminants is recommended.
- Areas of wear or damage may be repaired by ensuring that the area is dry and clean, and reapplying sealer to the affected areas at the recommended coverage rates.

PRECAUTIONS

- Ensure substrate is completely dry before application.
- Ensure adequate surface preparation is carried out to allow even application.
- Ensure a trial patch is applied to ensure suitability, required slip resistance and desired result is achieved.
- Ensure any existing coatings are compatible or removed prior to application.
- Do not apply during periods of extreme weather conditions – temperature or humidity. Apply between 5⁰c and 35⁰c and less than 85% humidity. To check these conditions, refer to <http://www.bom.gov.au>

TRANSPORT AND STORAGE

- | | | | |
|------------------|----------------------|------------------------|-----------------------|
| • Size: 3.5L, 8L | • Weight: 3.5kg, 8kg | • Cool and Dry Storage | • UN Number: 1263 |
| • DG Class: 3 | • Flash Point: 43°C | • Hazchem Code: 3Y | • Poisons Schedule: 5 |

**SAFETY AND FIRST AID**

Crommelin® DiamondCoat® Sealer Tint Base Safety Data Sheet is available from Crommelin® upon request.

Safety

- Ensure good ventilation and avoid breathing vapours.
- Avoid skin and eye contact. Wear gloves and eye protection. Remove splashes on skin immediately and remove contaminated clothing.
- Keep out of reach of children.
- Keep container sealed when not in use.
- Do not swallow.

First Aid

- If poisoning occurs, contact a doctor or poisons information centre: Ph 13 11 26.
- If swallowed, do not induce vomiting. Give a glass of water to drink.
- If in eyes, hold eyes open and flood with water for at least 15 minutes.
- If not breathing, apply artificial respiration.

Crommelin® and other marks followed by ® are registered trademarks.

Any advice, recommendation, information, assistance or service provided by Crommelin® in relation to its products or their use is given in good faith, however is provided without responsibility or liability.

Customers need to undertake their own assessment to determine the suitability of a product for the intended use. As the performance of any product is subject to a wide variety of different surface types as well as environmental and surface-specific conditions, it is essential that a sample of the product be applied to the intended area of use to ensure it is acceptable in appearance and finish and that it performs as required on the specific surface.

Crommelin® also reserves the right to update information without prior notice, to reflect ongoing research and product development.

