

Technical Data Sheet

Blackseal

Waterproofing

7 Day Technical Support 1800 655 711

Testing Approvals: AS 4020: 2005 – Products for Use in Contact with Drinking Water

Description			
<p>Blackseal is a waterborne bitumen emulsion modified with a synthetic rubber co-polymer to provide excellent waterproofing properties with good flexibility. VOC Content of Blackseal is below the maximum VOC Content for Architectural and Interior Sealants as required by Green Star Office Design V2, V3, Office Interiors V1.1, and APAS D181.</p>			
Features and Benefits			
<ul style="list-style-type: none"> • Quick drying • Flexible • Non flammable 		<ul style="list-style-type: none"> • Remains watertight under permanently wet conditions • Strong adhesion • Easy to apply 	
Area of Use			
<ul style="list-style-type: none"> • Retaining walls and decks • Planter boxes 		<ul style="list-style-type: none"> • Terracotta pots • Gutters 	
Technical Data			
Number of Coats:	2	Curing time:	7 days
Spreading Rate Per Coat:	1.5m ² /L	Colour:	Dark Brown
Wet Film Per Coat:	500 microns	Thinner:	Water
Recoat (@25°C):	2-4 hours	Shelf Life:	12 months
VOC Content (SCAQMD 304-91)	2g/L		
Application Guide			
<p>Surface Preparation</p> <ul style="list-style-type: none"> • Surfaces must be clean, sound, dry and free of dust. • Corroded metal areas should be wire brushed and treated with an anti-corrosive primer. • Prime highly absorbent surfaces with 1 part Blackseal diluted with 5 parts of water. <p>Application Procedure and Equipment</p> <ul style="list-style-type: none"> • Stir product well. • Apply to surface by brush, roller or airless spray gun. Soft brooms can be used on retaining walls. 			
Precautions			
<ul style="list-style-type: none"> • Do not apply when temperature is below 10°C or above 85% relative humidity, or if rain is imminent. • Do not use in applications under hydrostatic pressure. • Temporarily protect the membrane from mechanical damage after application using polystyrene boards or an equally effective alternative. • A cement screed or topping may be laid over the system after 24 hours curing. • When applying Blackseal to a retaining wall do not fill soil above level of application. Ensure that Blackseal is protected from damage when backfilling. • Blackseal remains water soluble until completely cured. • Externally where no topping is intended, the system must be over coated with an U.V. stable acrylic coating. 			

Technical Data Sheet

Blackseal

Waterproofing

7 Day Technical Support 1800 655 711

Cleaning

- Clean all equipment in water immediately after use.
- If **Blackseal** has dried on equipment, it may be removed with mineral turpentine and rinsed clean with detergent and water.

Health and Safety

Safety Precautions

- Provide good ventilation – open windows and doors and use circulating fans.
- If product is splashed on skin it should be washed off with water before it can dry.
- Wear gloves and eye protection during application.

First Aid

Swallowed: Contact a doctor or Poisons Information Centre. Do not induce vomiting. Give water to drink.

Eye: Gently flush with running water, holding eyelids open for 15 mins. Seek medical attention.

For detailed information refer to product label and the current Material Safety Data Sheet available from Crommelin.

In the case of an emergency please call the Poisons Information Centre on 13 11 26

Transport and Storage

Sizes:	20L	Flash Point:	N/A
Weights:	21.5Kg	UN Number:	N/A
Dangerous Goods Class:	N/A		

Disclaimer

Crommelin® and other marks followed by ® are registered trademarks. Marks followed by the symbol of ™ are trademarks. Any advice, recommendation, information, assistance or service provided by Crommelin® in relation to its products or their use is given in good faith, however is provided without responsibility or liability. Customers need to undertake their own assessment to determine the suitability of a product for the particular use intended. As the performance of any product is subject to a wide variety of different surface types as well as environmental and surface-specific conditions, it is essential that a sample of the product be applied to the intended area of use to ensure it is acceptable in appearance and finish and that it performs on the specific surface.