



PRO-300 WP

Balcony & Deck

Waterproof membrane, permanently flexible.

DESCRIPTION

Crommelin[®] PRO-300 WP is a high performance, synthetic rubber, heavy duty, reinforced liquid applied waterproofing membrane capable of accommodating structural movement.

Suitable for use in all above ground, non-UV exposed situations. Formulated for areas of permanent water immersion such as podium decks, roof terraces, slab edge waterproofing, fire tanks and balconies etc. Suitable for over-coating with renders, screeds, tiles or acrylic paints.

FEATURES AND BENEFITS

- Permanently flexible to accommodate structural movement.
- Seamless application for leak free performance.
- Class III high elongation over 300%.
- Primer less application (to well consolidated and dust free surfaces).
- Suitable for over-coating with screeds, renders, tiles and water based coatings.
- AS4858 – Class III.
- Green Star – Design & As Built v1.1: Indoor Pollutants 13.1.
- APAS 181 – Low VOC limits.
- AS4654 – Waterproofing external above ground building elements.

AREAS OF USE

PRO-300 WP is suitable for use in the following areas:

- Podium decks
- Slab edge waterproofing
- Balconies
- Roof terraces
- Fire tanks

SUITABLE SUBSTRATES

PRO-300 WP is suitable for use on the following surfaces:

- Concrete, masonry & cement renders.
- CFC sheeting and lightweight aggregate blocks.
- Timber & plywood sheeting.
- Steel – suitably prepared.

APPLICATION TOOLS

- Crommelin[®] Contractor Membrane Applicator Brush – 100mm, 75mm.
- Crommelin[®] Contractor Membrane Roller Cover – 230mm.

SURFACE PREPARATION

Full surface preparation instructions can be found at www.crommelin.com.au/full-instructions/

- Concrete must have cured for at least 28 days, screeds and renders 7 days.
- The surface should have a light even texture. Masonry should be flush pointed and all defects in existing surfaces made good.
- **Surfaces must be clean**, dry, sound and free from dust, grease, curing compounds, release agents, loose particles, efflorescence, concrete laitance or any other contaminants.
- Corroded metal should be wire brushed and treated with an anti-corrosion primer.
- All high points and protrusions should be removed, blow-holes and areas of honeycombing should be filled and the surface should be brought back to an even profile using a suitable repair mortar.
- **All surfaces must be dry.** A moisture test is required 100% of the time to ascertain if the substrate is dry enough to coat. Electronic moisture meters are recommended.
- If minor surface consolidation is required, apply 1 coat of 1:1 dilution of **PRO-300 WP** and water and allow to dry.
- If a greater amount of surface consolidation is required, apply one coat of **Crommelin[®] Powerflex** as per recommended application rates.
- If substrate is not dry, prime surface with **Crommelin[®] Dampstop** as per specifications.

PRODUCT PREPARATION

- **PRO-300 WP** is ready to use, simply stir well prior to application.

APPLICATION CONDITIONS

- Do not apply if surface/ambient temperatures are too high or too low. Recommended temperature range 7⁰c - 35⁰c.
- Do not apply if humidity is too high, or likely to be during the initial cure phase. Maximum recommended humidity during application and cure is 85%.
- Weather details may be checked at <http://www.bom.gov.au>.

APPLICATION PROCESS

Full application instructions can be found at www.crommelin.com.au/full-instructions/

- Bond breaking sealant/tape to all joints, junctions, protrusions, angles and internal corners must be used. The use of **Crommelin[®] Polyurethane Sealant**, **Crommelin[®] Silicone WP Plus** or **Crommelin[®] Reinforcing Fabric with Bond Breaker** is recommended.
- The use of **Crommelin[®] Reinforcing Fabric** is also recommended for use at all junctions to protect vulnerable areas from damage.
- Apply first coat evenly, as per recommended coverage rate and allow to dry.
- Re-coat when touch dry, after approximately 1 hour.
- Apply second coat evenly, at 90° (right angles) to first coat and allow to dry.
- Ensure membrane is protected from damage before over-coating.

RE-COAT/DRYING TIME @ 25°C / 50% RH

- Recoat time: 1 hour.
- Over-coat: 24 hours.
- Flood test: 48 hours.
- Full cure: 7 days.
- Ensure good airflow to optimise membrane cure time.

COVERAGE

- 2m² / L per coat – minimum 2 coats required.
- Wet film thickness: 500 microns.
- Complex or highly irregular surfaces may require additional coats.

CLEAN UP

- Clean all equipment with water before product dries.
- Uncured material may be removed with warm water and detergent.

SIZES

PRO-300 WP is available in 15L pails.

- 15L produces 15m² of finished membrane.

RELATED PRODUCTS

- Crommelin[®] Moisture Meter.
- Crommelin[®] Contractor Membrane Applicator Brush – 100mm, 75mm.
- Crommelin[®] Contractor Membrane Roller Cover – 230mm.
- Crommelin[®] Dampstop.



PRECAUTIONS

- Ensure substrate is completely dry before application.
- Ensure adequate surface preparation is carried out to allow even application.
- Ensure a trial patch is applied to ensure suitability and desired result is achieved.
- Do not apply during periods of extreme weather conditions – temperature or humidity. Apply between 7⁰c and 35⁰c and less than 85% humidity. To check these conditions, refer to <http://www.bom.gov.au>

WARRANTIES

- A standard warranty period of 10 years is offered for Crommelin[®] PRO-300 WP[®].
- Extended warranties are available for project specific applications. Please contact your Crommelin[®] representative, or the Crommelin[®] technical support team for detailed specifications applicable to your project and warranty requirements.

TRANSPORT AND STORAGE

- | | | | |
|-----------------|--------------------|------------------------|-------------------------|
| • Size: 15L | • Weight: 19kg | • Cool and Dry Storage | • UN Number: N/A |
| • DG Class: N/A | • Flash Point: N/A | • Hazchem Code: N/A | • Poisons Schedule: N/A |

PRODUCT APPEARANCE

- PRO-300 WP is sandstone in colour.

SAFETY AND FIRST AID

Crommelin[®] PRO-300 WP Safety Data Sheet is available from Crommelin[®] upon request.

Safety

- Ensure good ventilation and avoid breathing vapours.
- Avoid skin and eye contact. Wear gloves and eye protection. Remove splashes on skin immediately and remove contaminated clothing.
- Keep out of reach of children.
- Keep container sealed when not in use.
- Do not swallow.

First Aid

- If poisoning occurs, contact a doctor or poisons information centre: Ph. 13 11 26.
- If swallowed, do not induce vomiting. Give a glass of water to drink.
- If in eyes, hold eyes open and flood with water for at least 15 minutes.
- If not breathing, apply artificial respiration.

Crommelin[®] and other marks followed by ® are registered trademarks.

Any advice, recommendation, information, assistance or service provided by Crommelin[®] in relation to its products or their use is given in good faith, however is provided without responsibility or liability.

Customers need to undertake their own assessment to determine the suitability of a product for the intended use. As the performance of any product is subject to a wide variety of different surface types as well as environmental and surface-specific conditions, it is essential that a sample of the product be applied to the intended area of use to ensure it is acceptable in appearance and finish and that it performs as required on the specific surface.

Crommelin[®] also reserves the right to update information without prior notice, to reflect ongoing research and product development.